

## CLAIMS

We claim:

1. A corrosion-inhibited fire retardant composition comprising:
  - at least one fire retardant comprised of at least one ammonium
  - 5 polyphosphate;
  - at least one biopolymer having a particle size diameter less than about 100 microns; and
  - a corrosion inhibiting system comprised of at least one corrosion
  - inhibiting compound selected from a group of corrosion inhibiting compounds
  - 10 consisting of azoles, insoluble ferric pyrophosphate, soluble ferric pyrophosphate, ferrous oxalate, ferric citrate, ferrous sulfate, ferric ammonium citrate, soluble ferric orthophosphate, insoluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate, ferrous bromide, ferrous
  - 15 gluconate, ferrous iodide, ferric acetate, ferric fluoroborate, ferric hydroxide, ferric oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate, and any combination thereof;
  - wherein said corrosion inhibiting system is present in a minor amount effective to substantially reduce corrosiveness of said fire retardant composition.
- 20 2. The composition of claim 1 wherein said azole is at least one azole selected from a group of azoles including tolytriazole, benzotriazole, mercaptobenzothiazole, dimercaptothiadiaazole, 1,2 benzisothiazoline-3-1, 2-benzimidazolone, 4,5,6,7-tetrahydrobenzotriazole, tolylimidazole, 2-(5-ethyl-2-pyridyl) benzimidazole, phthalimide, any alkali metal salts thereof and
- 25 combinations thereof.

3. The composition of claim 1 further comprising at least one additive selected from a group of additives consisting of suspending agents, fugitive coloring agents, non-fugitive coloring agents, surfactants, stabilizers, corrosion inhibitors, opacifying pigments and any combination thereof.

5 4. The composition of claim 1 wherein said corrosion inhibitor is at least one azole and said azole is present in said corrosion-inhibited fire retardant composition, in concentrate, in a minor amount effective to obtain a maximum corrosivity of yellow brass to a maximum of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-10 304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

15 5. The composition of claim 1 wherein said coloring agent is at least one coloring agent selected from a group of coloring agents consisting of fugitive coloring agents, opacifying pigments, and highly colored coloring agents.

6. The composition of claim 3 wherein said suspending agent is at least one suspending agent selected from a group of suspending agents consisting of attapulgus, sepiolite, fuller's earth, montmorillonite, and kaolin clay.

20 7. The composition of claim 1 wherein said corrosion inhibiting system is comprised of at least one soluble corrosion inhibiting compound and at least one insoluble corrosion inhibiting compound.

25 8. The composition of claim 1 wherein said corrosion inhibiting system is present in a minor amount effective in said corrosion-inhibited fire retardant composition, in concentrate, to obtain at least one of a maximum corrosivity to

41482/25424

aluminum of 5.0 mils per year per year, yellow brass of 5.0 mils per year, and steel of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long  
5 Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

9. The composition of claim 1 further comprising water.

10. The composition of claim 1 wherein said corrosion inhibiting system comprises in the range of about .01% to about 10% of said corrosion-inhibited fire  
10 retardant composition.

11. The composition of claim 1 wherein said corrosion inhibiting system comprises in the range of about .30% to about 6.0% of said corrosion-inhibited fire retardant composition.

12. The composition of claim 1 wherein said corrosion inhibiting system  
15 comprises in the range of about 0.6% to about 5.0% of said corrosion-inhibited fire retardant composition.

13. The composition of claim 1 comprising in the range of about .01% to about 5.0% said biopolymer.

14. The composition of claim 1 comprising in the range of about 1.0% said  
20 biopolymer.

15. The composition of claim 1 further comprising at least one guar biopolymer.

16. The composition of claim 1 wherein said biopolymer is at least one biopolymer selected from a group of biopolymers consisting of rhamosan, xanthan and welan biopolymers.

FOOTNOTES

41482/25424

17. The composition of claim 16 wherein said biopolymer is at least one xanthan biopolymer.

18. The composition of claim 17 wherein said xanthan biopolymer comprises about 1% of said corrosion-inhibited fire retardant composition.

5 19. The composition of claim 1 comprising in the range of about 2% to about 3% ferric pyrophosphate.

20. The composition of claim 1 comprising in the range of about 2% to about 3% ferric pyrophosphate and about 1% xanthan biopolymer.

21. The composition of claim 1 comprising in the range of about 1% to about 2%  
10 iron oxide, about 2% to about 3% ferric pyrophosphate, about 1% xanthan biopolymer, about 1% to about 2% attapulgus clay, and about .01% to about 1% tolytriazole.

22. A corrosion-inhibited fire retardant composition comprising:

15 at least one fire retardant comprised of at least one ammonium polyphosphate;  
attapulgus clay;  
at least one xanthan biopolymer having a particle size less than about 100 microns;

20 at least one additive selected from a group of additives consisting of suspending agents, coloring agents, surfactants, stabilizers, corrosion inhibitors, opacifying pigments and any combination thereof; and

25 a corrosion inhibiting system comprised of at least one corrosion inhibiting compound selected from a group of corrosion inhibiting compounds consisting of azoles, insoluble ferric pyrophosphate, soluble ferric pyrophosphate, ferrous oxalate, ferric citrate, ferrous sulfate, ferric ammonium citrate, soluble

41482/25424

ferric orthophosphate, insoluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate, ferrous bromide, ferrous gluconate, ferrous iodide, ferric acetate, ferric fluoroborate, ferric oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate, and any combination thereof;

wherein said corrosion inhibiting system is present in a minor amount effective to reduce corrosiveness of said ammonium polyphosphate to a maximum corrosivity to aluminum of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service; and

wherein said biopolymer comprises in the range of about 0.01% to about 5.0% of said fire retardant composition.

23. A method of preparing a corrosion-inhibited fire retardant composition, adapted for aerial application to wildland fires, the method comprising the steps of:

(a) forming an intermediate concentrate composition comprising:

(i) a fire retardant composition comprised of at least one ammonium polyphosphate;

(ii) a corrosion inhibiting system comprised of at least one corrosion inhibiting compound selected from a group of corrosion inhibiting compounds consisting of azoles, insoluble ferric pyrophosphate, soluble ferric

41482/25424

pyrophosphate, ferrous oxalate, ferric citrate, ferrous sulfate, ferric ammonium citrate, soluble ferric orthophosphate, insoluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate,  
5 ferrous bromide, ferrous gluconate, ferrous iodide, ferric fluoroborate, ferric hydroxide, ferric hydroxide, ferric oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate, and any combination thereof; and

at least one biopolymer having a particle size less than about 100 microns; wherein said corrosion inhibiting system is present in a minor amount effective  
10 to substantially reduce corrosiveness of said fire retardant composition; and

(b) diluting said intermediate concentrate with water to form said corrosion-inhibited fire retardant composition.

24. The method of claim 23 wherein said azole is at least one azole selected from a group of azoles including tolytriazole, benzotriazole, mercaptobenzothiazole,  
15 dimercaptomthiadiazole, 1,2 benzisothiazoline-3-1, 2-benzimidazolone, 4,5,6,7-tetrahydrobenzotriazole, tolylimidazole, 2-(5-ethyl-2-pyridyl) benzimidazole, phthalimide, any alkali metal salts thereof and combinations thereof.

25. The method of claim 23 wherein said corrosion inhibiting system is comprised of at least one soluble corrosion inhibiting compound and at least one  
20 insoluble corrosion inhibiting compound.

26. The method of claim 23 wherein said intermediate concentrate composition further comprises at least one additive selected from a group of additives consisting of suspending agents, coloring agents, surfactants, stabilizers, corrosion inhibitors, opacifying pigments and any combination thereof.

27. The method of claim 23 wherein said corrosion inhibiting system comprises at least one azole and said azole is present in said corrosion-inhibited fire retardant composition, in concentrate, in a minor amount effective to obtain a maximum corrosivity to yellow brass of 5.0 mils per year, as determined by the  
5 "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

10 28. The method of claim 23 wherein said corrosion inhibiting system is present in a minor amount effective to reduce the corrosiveness of said fire retardant composition, in concentrate, to at least one of a maximum corrosivity to aluminum of 5.0 mils per year, brass of 5.0 mils per year and steel of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1  
15 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

29. The method of claim 23 wherein said intermediate concentrate composition  
20 is diluted such that a maximum corrosivity of aluminum is 2.0 mils per year and the maximum corrosivity of brass and steel is 2.0 mils per year when tested in the totally immersed condition and 5.0 mils per year when tested in the partially immersed condition, as specified and determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000)  
25 Superseding Specification 5100-00304a (February 1986)," entitled "Specification

FOUO 20080606

for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

- 5
30. The method of claim 23 wherein said coloring agent is at least one coloring agent selected from a group of coloring agents consisting of fugitive coloring agents, opacifying pigments, and highly colored coloring agents.
31. The method of claim 26 wherein said suspending agent is at least one suspending agent selected from a group of suspending agents consisting of attapulugus clay, sepiolite, fuller's earth, montmorillonite, and kaolin clay.
- 10 32. The method of claim 23 wherein said fire retardant composition comprises in the range of about .01% to about 5.0% said biopolymer.
33. The method of claim 23 wherein said fire retardant composition comprises in the range of about 1.0% said biopolymer.
34. The method of claim 23 wherein said fire retardant composition further comprises at least one guar biopolymer.
- 15 35. The method of claim 23 wherein said biopolymer is at least one biopolymer selected from a group consisting of a xanthan rhamsan and welan biopolymers.
36. The method of claim 35 wherein said biopolymer is a xanthan biopolymer.
37. The method of claim 36 wherein said xanthan biopolymer comprises about 1% of said corrosion-inhibited fire retardant composition.
- 20 38. The method of claim 23 wherein said step of forming an intermediate concentrate comprises forming a concentrate comprising in the range of about 2% to about 3% ferric pyrophosphate.
39. The method of claim 23 wherein said step of forming an intermediate concentrate comprises forming a concentrate comprising in the range of about 2% to about 3% ferric pyrophosphate and about 1% xanthan biopolymer.
- 25

09978800-101001



40. The method of claim 23 wherein said step of forming an intermediate concentrate comprises forming a concentrate comprising in the range of about 1% to about 2% iron oxide, about 2% to about 3% ferric pyrophosphate, about 1% xanthan biopolymer, about 2% attapulgus clay, and about .01% to about 1% tolytriazole.

41. A method of preparing a corrosion-inhibited fire retardant composition, adapted for aerial application to wildland fires, the method comprising the steps of:

(a) forming an intermediate concentrate composition comprising:

(i) at least one fire retardant comprised of at least one ammonium polyphosphate;

(ii) attapulgus clay;

(iii) a corrosion inhibiting system comprised of at least one corrosion inhibiting compound selected from a group of corrosion inhibiting compounds consisting of azole, insoluble ferric pyrophosphate, soluble ferric pyrophosphate, insoluble ferrous oxalate, soluble ferric citrate, soluble ferrous sulfate, insoluble ferric ammonium citrate, insoluble ferric orthophosphate, soluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate, ferrous bromide, ferrous gluconate, ferrous iodide, ferric fluoroborate, ferric hydroxide, ferric oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate, and any combination thereof; and

at least one xanthan biopolymer having a particle size of less than about 100 microns;

0997888-10101  
FOOT-209260

wherein said corrosion inhibiting system is present in a minor amount effective to reduce the corrosiveness of said fire retardant composition, in concentrate, to aluminum of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000)

5 Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service; and wherein said fire retardant composition comprises in the range of about .01% to about 5.0% said xanthan biopolymer prior to dilution; and

10 (b) diluting said intermediate concentrate with water to form said corrosion-inhibited fire retardant composition such that a maximum corrosivity of aluminum is 2.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification  
15 for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

42. A method of suppressing wildland fires comprising a method of applying to wildland vegetation a fire suppressing composition comprising:

water; and

20 a corrosion-inhibited fire retardant composition comprising:

at least one fire retardant composition comprised of at least one ammonium polyphosphate;

at least one biopolymer having a particle size of less than about 100 microns;

25 and

FOUO 2004050

a corrosion inhibiting system comprising at least one corrosion inhibiting compound selected from a group of corrosion inhibiting compounds consisting of azoles, insoluble ferric pyrophosphate, soluble ferric pyrophosphate, ferrous oxalate, ferric citrate, ferrous sulfate, ferric ammonium citrate, soluble ferric orthophosphate, insoluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate, ferrous bromide, ferrous gluconate, ferrous iodide, ferric acetate, ferric fluoroborate, ferric hydroxide, ferric oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate, and any combination thereof;

wherein said corrosion inhibiting system is present in a minor amount effective to substantially reduce the corrosiveness of said fire retardant composition.

43. The method of claim 42 wherein said azole is at least one azole selected from a group of azoles including tolytriazole, benzotriazole, mercaptobenzothiazole, dimercaptomthiadiazole, 1,2 benzisothiazoline-3-1, 2-benzimidazolone, 4,5,6,7-tetrahydrobenzotriazole, tolylimidazole, 2-(5-ethyl-2-pyridyl) benzimidazole, phthalimide, any alkali metal salts thereof and combinations thereof.

44. The method of claim 42 further comprising at least one additive selected from a group of additives consisting of suspending agents, coloring agents, surfactants, stabilizers, corrosion inhibitors, opacifying pigments, and any combination thereof.

45. The method of claim 42 wherein said corrosion inhibitor is at least one azole and said azole is present in said corrosion-inhibited fire retardant composition, in concentrate, in a minor amount effective to obtain a corrosivity to yellow brass of a maximum of 5.0 mils per year, as determined by the "Uniform Corrosion" test

41482/25424

set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.

- 5 (46) The method of claim 42 wherein said coloring agent is at least one coloring agent selected from a group of coloring agents consisting of fugitive coloring agents, opacifying pigments and highly colored colorants.
- (47) The method of claim 44 wherein said suspending agent is at least one selected from a group of suspending agents consisting of attapulgus clay, sepiolite, 10 fuller's earth, montmorillonite, and kaolin clay.
- (48) The method of claim 42 wherein said corrosion inhibiting system is comprised of at least one soluble corrosion inhibiting compound and at least one insoluble corrosion inhibiting compound.
- (49) The method of claim 42 wherein said corrosion inhibiting system is present 15 in a minor amount effective to reduce the corrosiveness of said fire retardant composition, in concentrate, to at least one of a maximum corrosivity to aluminum of 5.0 mils per year, brass of 5.0 mils per year, and steel of 5.0 mils per year, as determined by the "Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b (January 2000) Superseding Specification 20 5100-00304a (February 1986)," entitled "Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground Application," issued by the United States Department of Agriculture, Forest Service.
- (50) The method of claim 42 wherein said corrosion inhibiting system comprises 25 in the range of about .01% to about 10.0% of said corrosion-inhibited fire retardant composition.

51. The method of claim 42 wherein said corrosion inhibiting system comprises in the range of about .30% to about 6.0% of said corrosion-inhibited fire retardant composition.
52. The method of claim 42 wherein said corrosion inhibiting system comprises  
5 in the range of about .60% to about 5.0% of said corrosion-inhibited fire retardant composition.
53. The method of claim 42 wherein said corrosion-inhibited fire retardant composition comprises in the range of about .01% to about 5.0% said biopolymer.
54. The method of claim 53 wherein said corrosion-inhibited fire retardant  
10 composition comprises in the range of about 1.0% said biopolymer.
55. The method of claim 42 wherein said biopolymer is at least one biopolymer selected from a group consisting of xanthan, rhamosan and welan biopolymers.
56. The method of claim 42 wherein said corrosion-inhibited fire retardant composition further comprises at least one guar biopolymer.
- 15 57. The method of claim 55 wherein said biopolymer is a xanthan biopolymer.
58. The method of claim 57 wherein said xanthan biopolymer comprises about 1% said corrosion-inhibited fire retardant composition.
59. The method of claim 42 wherein said step of aeriually applying a fire suppressing composition comprises aeriually applying a fire suppressing  
20 composition comprising in the range of about 2% to about 3% ferric pyrophosphate.
60. The method of claim 42 wherein said step of aeriually applying a fire suppressing composition comprises applying a fire suppressing composition comprising in the range of about 2% to about 3% ferric pyrophosphate and about  
25 1% biopolymer.

FBI/DOJ - 2022-0650

61. The method of claim 42 wherein said step of aerially applying a fire suppressing composition comprises applying a fire suppressing composition comprising in the range of about 1% to about 2% iron oxide, about 2% to about 3% ferric pyrophosphate, about 1% xanthan biopolymer, about 2% attapulgus clay, and about .01% to about 1% tolytriazole.

62. A method of suppressing wildland fires comprising aerially applying to wildland vegetation a fire suppressing composition comprising:

- water; and
- a corrosion-inhibited polyphosphate composition comprising:
  - at least one ammonium polyphosphate;
  - attapulgus clay;
  - in the range of about .01% to about 5.0% at least one xanthan gum having a particle size less than 100 microns;
  - at least one additive selected from a group of additives consisting of coloring agents, surfactants, stabilizers, corrosion inhibitors, and any combination thereof; and
  - a corrosion inhibiting system comprised of at least one corrosion inhibiting compound selected from a group of corrosion inhibiting compounds consisting of insoluble ferric pyrophosphate, soluble ferric pyrophosphate, ferrous oxalate, ferric citrate, ferrous sulfate, ferric ammonium citrate, soluble ferric orthophosphate, insoluble ferric orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate, ferrous ammonium sulfate, ferrous bromide, ferrous gluconate, ferrous iodide, ferric acetate, ferric fluoroborate, ferric hydroxide, ferric

099888-10164  
FOOT-209260

41482/25424

oleate, ferrous fumarate, ferrous oxide, ferric lactate, ferric resinate and any combination thereof;

wherein said corrosion inhibiting system is present in a minor amount effective to reduce corrosiveness to said ammonium polyphosphate, in concentrate, to a  
5 maximum corrosivity to aluminum of 5.0 mils per year, as determined by the  
"Uniform Corrosion" test set forth in Section 4.5.6.1 of "Specification 5100-304b  
(January 2000) Superseding Specification 5100-00304a (February 1986)," entitled  
"Specification for Long Term Retardant, Wildland Fire, Aircraft or Ground  
Application," issued by the United States Department of Agriculture, Forest  
10 Service.

63. A method of inhibiting corrosion comprising:

providing a corrodible material; and

contacting said corrodible material with a composition for inhibiting  
corrosion comprising at least one biopolymer having a particle size less than  
15 about 100 microns and an effective amount of a corrosion inhibiting system  
comprised of at least one corrosion inhibiting compound selected from a group of  
corrosion inhibiting compounds consisting of azoles, insoluble ferric  
pyrophosphate, soluble ferric pyrophosphate, ferrous oxalate, ferric citrate, ferrous  
sulfate, ferric ammonium citrate, soluble ferric orthophosphate, insoluble ferric  
20 orthophosphate, ferric ammonium oxalate, ferric ammonium sulfate, ferric  
bromide, ferric sodium oxalate, ferric stearate, ferric sulfate, ferrous acetate,  
ferrous ammonium sulfate, ferrous bromide, ferrous gluconate, ferrous iodide,  
ferric acetate, ferric fluoroborate, ferric hydroxide, ferric oleate, ferrous fumarate,  
ferrous oxide, ferric lactate, ferric resinate and any combination thereof.

64. The method of claim 63 wherein said azole is at least one azole selected from a group of azoles including tolytriazole, benzotriazole, mercaptobenzothiazole, dimercaptomthiadiazole, 1,2 benzisothiazoline-3-1, 2-benzimidazolone, 4,5,6,7-tetrahydrobenzotriazole, tolylimidazole, 2-(5-ethyl-2-pyridyl) benzimidazole,  
5 phthalimide, any alkali metal salts thereof and combinations thereof.

65. The method of claim 63 wherein said corrosion inhibiting system is comprised of at least one soluble corrosion inhibiting compound and at least one insoluble corrosion inhibiting compound.

66. The method of claim 63 wherein said corrosion inhibiting system further  
10 comprises at least one additive selected from a group of additives consisting of suspending agents, coloring agents, opacifying pigments, surfactants, stabilizers, corrosion inhibitors, and any combination thereof.

67. The method of claim 63 wherein said corrodible material is at least one material selected a group of corrodible materials consisting of steel, brass and  
15 aluminum.

68. The method of claim 63 wherein said corrosion inhibiting system further comprises water.

69. The method of claim 66 wherein said suspending agent is at least one selected from a group of suspending agents consisting of attapulugus clay, Fuller's  
20 earth, montmorillonite, sepiolite and kaolin clay.

70. The method of claim 63 wherein said step of contacting said corrodible material with at one biopolymer comprises contacting in the range of about .01% to about 5.0% of said biopolymer is contacted with said corrodible material.

71. The method of claim 70 wherein about 1.0% of said biopolymer is contacted  
25 with said corrodible material.



72. The method of claim 63 wherein said biopolymer is at least one biopolymer selected from a group including xanthan, rhamosan and welan biopolymers.

73. The method of claim 63 whereby no guar gum is contacted with said corrodible material.

5 74. The method of claim 72 wherein said biopolymer is a xanthan biopolymer.

75. The method of claim 74 wherein said step of contacting said corrodible material with said composition comprises contacting said material with said composition, wherein said xanthan biopolymer comprises about 1% of said composition.

10 76. The method of claim 63 wherein said step of contacting said corrodible material with said composition comprises contacting said material with said composition, wherein said composition comprises in the range of about 2% to about 3% ferric pyrophosphate.

15 77. The method of claim 63 wherein said step of contacting said corrodible material with said composition comprises contacting said material with said composition, wherein said composition comprises in the range of about 2% to about 3% ferric pyrophosphate and about 1% xanthan biopolymer.

20 78. The method of claim 63 wherein said step of contacting said corrodible material with said composition comprises contacting said material with said composition, wherein said composition comprises about 1% to about 2% iron oxide, about 2% to about 3% ferric pyrophosphate, about 1% xanthan biopolymer, about 1% to about 2% attapulugus clay, and about .01% to about 1% tolytriazole.

25 79. A method of inhibiting corrosion comprising: providing a corrodible material, and contacting said corrodible material with a composition for inhibiting corrosion comprising in the range of about .01% to about 5.0% at least one

41482/25424

xanthan gum having a particle size less than 100 microns and an effective amount of a corrosion inhibiting system comprised of ferric pyrophosphate.

FOR 202450